



Specification Sheet

Material	Premium SBR Rubber Sheet
BRP Style	AA515
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	ASTM D2000 M4AA507A13B13

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	50±5
Tensile, Original	ASTM D412 - PSI Min	1,000
Elongation, Original	ASTM D412 - %	400

Heat Aged, Test Method D 573, 70 h @ 70°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	- 50 % Max
Hardness Change	Points	± 15 Max

Oil Immersion Test Method D471 IRM 903 Oil 70h @ 70° C

		No Requirement
--	--	----------------

Compression Set, Test Method ASTM D395 Solid, max, % 22 h @ 70 C

Compression Set	%	50% Max
-----------------	---	---------

Effective Temperature Range -20°F to 212° F