



## Specification Sheet

<b>Material</b>	<b>Gray Premium EPDM Rubber Sheet</b>
BRP Style	5479 - 60 Durometer EPDM
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	ASTM D2000 3BA615A14B13C12F17Z, Z= Gray

## Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	60±5
Tensile, Original	ASTM D412 - PSI Min	1,500
Elongation, Original	ASTM D412 - %	350

## Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	- 50 % Max
Hardness Change	Points	± 15 Max

## Oil Immersion

		No Requirement
--	--	----------------

## Compression Set, Test Method ASTM D395 Solid, max, % 22 h @ 70 C

Compression Set	%	50% Max
-----------------	---	---------

## Additional Requirements

### A14 - Heat Resistance, D573, 70 hours @ 100C°

Hardness Change	Points	+ 10
Tensile Change	PSI %	- 25 %Max
Elongation Change	% Max	- 25% Max

### B13 - Compression Set, Test Method D395 Method B, 22 h @ 70° C, max. %

Compression Set	% Max	25% Max
-----------------	-------	---------

**BRP Manufacturing Company**  
637 North Jackson Street  
Lima, Ohio 45802  
Phone: 419-228-4441  
Fax: 419-222-5010  
Toll free: 800-858-0482



---

**C12 - Resistance to Ozone, Test Method D1171**

		100
--	--	-----

---

**F17 - Low Temperature Resistance, Test Method D2137, Method A, 9.3.3, 3 min. @ -40 C°**

	Non-brittle after 3 min.	Pass
--	--------------------------	------