



Specification Sheet

Material	Neoprene Rubber Sheet - 100% Neoprene / Polychloroprene
BRP Style	BC725
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	2BC725A14B14C12EO14EO34F17

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	70 ±5
Tensile, Original	ASTM D412 - PSI Min	2,500
Elongation, Original	ASTM D412 - %	300

Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	-50% Max
Hardness Change	Points	± 15

Oil immersion, Test Method D471, IRM 903 Oil, 70 h @ 100°C

Volume	% Max	+120
--------	-------	------

Compression Set, Test Method ASTM D395 S, max, % 22 h @ 100C

Compression Set	%	80% Max
-----------------	---	---------

Additional Requirements

A14 - Heat Resistance, D573, 70 hours @ 100C°

Hardness Change	Points	+ 15
Tensile Change	PSI %	- 15 Max
Elongation Change	% Max	-40% Max

B14 - Compression Set, Test Method D395 Method B, 22 h @ 100°C, max. %

Compression Set	% Max	35% Max
-----------------	-------	---------



C12 - Resistance to Ozone, Test Method D1171

		100
--	--	-----

EO14 - Fluid Resistance, Test Method D471IRM 901 Oil, 70 h @ 100 C°

Hardness	Points	± 10
Tensile Change	PSI	- 30% Max
Elongation Change	% Max	-30% Max
Volume	% Max	-10 to +15

EO34 - Fluid Resistance, Test Method D471IRM 903 Oil, 70 h @ 100 C°

Tensile Change	PSI	- 70% Max
Elongation Change	% Max	- 55% Max
Volume	% Max	+120

F17 - Low Temperature Brittleness, Test Method D2137, Method A, 9.3.2, @-40 C°

	Non-brittle after 3 min.	Pass
--	--------------------------	------

Conforms to FMV-SS-302

Temperature Range -40°F to 220°F