

BRP Manufacturing Company
 637 North Jackson Street
 Lima, Ohio 45802
 Phone: 419-228-4441
 Fax: 419-222-5010
 Toll free: 800-858-0482



Specification Sheet

Material	Nitrile Rubber Sheet
BRP Style	BG615 - Style 793
Finish	Smooth
ASTM Callout	ASTM D2000 2 BG615A14B14EF21EO14EO34F17

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	60±5
Tensile, Original	ASTM D412 - PSI Min	1,500
Elongation, Original	ASTM D412 - %	500

Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	-20 % Max
Elongation Change	%	-25 % Max
Hardness Change	Points	± 10

Oil immersion, Test Method D471, IRM 903 Oil, 70 h @ 100°C

Volume Change	% Max	+40
---------------	-------	-----

Compression Set, Test Method ASTM D395 S, max, % 70 h @ 100C

Compression Set	%	50% Max
-----------------	---	---------

Additional Requirements

Heat Resistance, D573, 70 hours @ 100C°

Tensile Change	PSI	± 30% Max
Elongation Change	%	-50% Max
Hardness Change	Points	± 15

Compression Set, Test Method D395 Method B, 22 h @ 100°C, max. %

Compression Set	% Max	25% Max
-----------------	-------	---------

BRP Manufacturing Company
637 North Jackson Street
Lima, Ohio 45802
Phone: 419-228-4441
Fax: 419-222-5010
Toll free: 800-858-0482



Fuel Resistance, Test Method D471 Fuel B (25% Toluene), 168 h @ 23° C

Volume	% Max	30%
--------	-------	-----

Oil Resistance, Test Method D471 NO 3 Oil, 70 h @ 100 C° (EO14)

Volume	% Max	-0 to +7
--------	-------	----------

Oil Resistance, Test Method D471 NO 3 Oil, 70 h @ 100 C° (EO34)

Volume	% Max	-0 to +25
--------	-------	-----------

Low Temperature Brittleness, Test Method D2137 Method A, 9.2.2 non brittle after 3 mins. @ -40° C

		Pass
--	--	------

Operating Temperature Range -20° - 212° F

Also tested to EO15, EO35