



Specification Sheet

Material	Premium Grade 60 Duro Butyl Rubber Sheet
BRP Style	1C991
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	ASTM D2000 1AA615Z Basic Requirements, Z = Butyl

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	60±5
Tensile, Original	ASTM D412 - PSI Min	1,500
Elongation, Original	ASTM D412 - %	350

Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	- 50 % Max
Hardness Change	Points	± 15 Max

Oil Immersion

		No Requirement
--	--	----------------

Compression Set, Test Method ASTM D395 S, max, % 22 h @ 70 C

Compression Set	%	50% Max
-----------------	---	---------

BRP Butyl quality commercial sheet rubber is excellent for shock dampening applications in addition to those where gas permeability and high temperature tolerance are required.

Effective Temperature Range -40° to 220°