



## Specification Sheet

<b>Material</b>	<b>EPDM Rubber Sheet</b>
BRP Style	CE40
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	ASTM D2000 BA410

## Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	40±5
Tensile, Original	ASTM D412 - PSI Min	1,000
Elongation, Original	ASTM D412 - %	300

## Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	- 50 % Max
Hardness Change	Points	± 15 Max

## Oil Immersion

		No Requirement
--	--	----------------

## Compression Set, Test Method ASTM D395 Solid, max, % 22 h @ 70° C

Compression Set	%	50% Max
-----------------	---	---------

Temperature Range -40° F to 240° F