



Specification Sheet

| | |
|-----------------|---|
| Material | Cork Rubber Tape |
| BRP Style | CR180 and CR181 |
| Finish | Smooth / Buffed one side Fabric or PSA one side |
| ASTM Callout | None required |

Basic Requirements

| Requirement | Condition | Specification Requirements |
|--------------------|---|-----------------------------------|
| Hardness, Original | ASTM D2240 | 50-60 |
| Tensile, Original | ASTM D412 - PSI Min | 148 |
| Specific Gravity | | .8 to .9 |
| Compressibility | 78.5 pounds | 17-32 |
| Recovery | % | 95.4 |
| Thickness Swell | % | +2.8 |
| Weight Loss | % (permanent deflection retained) | -2.96 |
| Volume Swell | % (swell test conducted for 22 hours at room temperature in H ₂ O) | + 13.2 |

Low Temperature Resistance, Test Conditions 5 hours @ -40° F

| | | |
|--|---|------|
| | % | 16.6 |
|--|---|------|

CR180 is manufactured with a cloth back one side with PSA. This material conforms to the requirements of Mil-T-6841 and /or AMS-T-6841

CR181 is manufactured with cloth back one side without PSA. Without PSA the material cannot be certified to the military specification