



Specification Sheet

Material	Rubber Sheet
BRP Style	CV75
Finish	Smooth or Nylon
ASTM Callout	ASTM D2000 2HK710B38Z1, Z1=75 +/- 75

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	75±5
Tensile, Original	ASTM D412 – PSI Min	1,000
Elongation, Original	ASTM D412 – %	175

Heat Aged, Test Method D 573, 70 h @ 250°C

Hardness Change	Points	± 15
Tensile	Change %	± 30 %
Elongation	Change %	- 50%

Oil immersion, Test Method D471, IRM 903 Oil, 70 h @ 150°C

Volume Change	Change %	+ 10
---------------	----------	------

Compression Set, Test Method ASTM D395 plied max, % 22 h @ 175° C

Compression Set	%	35% Max
-----------------	---	---------

Additional Requirements

Compression Set, Test Method ASTM D395, Method B max, % 22 h @ 200° C

Compression Set	%	50% Max
-----------------	---	---------

ASTM D2000 2HK707B38Z1, Z1=75 +/- 75

Temperature Range -10F to 400F