



Specification Sheet

Material	HH-P-151 F Class 2 Cotton Inserted Neoprene (polychloroprene)
BRP Style	MX225
Finish	Smooth (Fabric Finish is Available)

Basic Requirements

Rubber

Requirement	Condition	Specification Requirements
Hardness Pts	ASTM D2240	70±5
Tensile, Original	ASTM D412 - PSI Min	1,500 PSI (10.3 MPa)
Elongation, Ultimate	ASTM D412 - %	250

Fabric

Requirement	Condition	Specification Requirements
Fabric		Cotton
Fabric Weight ounces	ASTM D412 - PSI Min	10-12 ounces per square yard
Elongation, Ultimate	ASTM D412 - %	250

Specified 1 ply per 1/16"

Operating Temperature -20° to 212° F