

# BRP Manufacturing Company

Rubber Sheet, Extruded, and Molded Products  
637 North Jackson Street  
Lima, OH 45802-0389  
800-858-0482  
Fax 419-222-5010  
www.brpmfg.com



## PRODUCT INFORMATION

### Specification Sheet - Style S5460

**Product** EPDM, White

<b>Specification</b>	3BA613A14B13C12F17Z1Z2Z3, Z1=White, Z2= CFR 177.2600 Title 21, Z3 = TSM 1500G N609O2
----------------------	-----------------------------------------------------------------------------------------

ASTM Standard	Condition	Requirement
Original Hardness	ASTM D2240 Shore A	60±5
Original Tensile	ASTM D 412	1,300 PSI (min.)
Original Elongation	ASTM D 412	300 % (min.)

Heat Aged	ASTM D573, 72 hrs. @ 70°C	
Change in Duro		+ 10 points MAX.
Change in Tensile		-25 % MAX
Change in elongation		-35 % MAX

<b>Oil Immersion</b>		No Requirement
----------------------	--	----------------

Meets CFR177.2600 Title 21 (FDA approved ingredients)

Operating Temperature -40° F to 240° F