



Specification Sheet

Material	EPDM Rubber Sheet
BRP Style	BA415
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	ASTM D2000 3BA415A14B13C12F19P2Z, Z= conforms to FMV-SS-302

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	40±5
Tensile, Original	ASTM D412 - PSI Min	1,500
Elongation, Original	ASTM D412 - %	400

Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	- 50 % Max
Hardness Change	Points	± 15 Max

Oil Immersion

		No Requirement
--	--	----------------

Compression Set, Test Method ASTM D395 S, max, % 22 h @ 70 C

Compression Set	%	50% Max
-----------------	---	---------

Additional Requirements

A14 - Heat Resistance, D573, 70 hours @ 100C°

Hardness Change	Points	+ 10
Tensile Change	PSI %	- 25 %Max
Elongation Change	% Max	- 25% Max

B13 - Compression Set, Test Method D395 Method B, 22 h @ 70° C, max. %

Compression Set	% Max	25% Max
-----------------	-------	---------



C12 - Resistance to Ozone, Test Method D1171

		100
--	--	-----

F19 - Low Temperature Resistance, Test Method D2137, Method C, 9.3.3 @ -55 C°

	Non-brittle after 3 min.	Pass
--	--------------------------	------

P2 - Stain Resistance Test Method D925, Method B, Control Panel

		100
--	--	-----

Z= conforms to FMV-SS-302

Operating Temperature -40° F to 240° F