



Specification Sheet

Material	Mil-G-1149 Type 1 Class 1
BRP Style	S765 (neoprene/ polychloroprene)
Finish	Smooth (Fabric Finish is Available)

Oil Resistant

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	50 ± 5
Tensile, Original	ASTM D412 - PSI Min	1000
Elongation, Original	ASTM D412 - %	300

Effective Operating Temperature -40 - 220° F