



Specification Sheet

Material	EPDM Rubber Sheet
BRP Style	BA315
Finish	Smooth (Fabric Finish is available on select products)
ASTM Callout	ASTM D2000 3BA315F17

Basic Requirements

Requirement	Condition	Specification Requirements
Hardness, Original	ASTM D2240	30±5
Tensile, Original	ASTM D412 – PSI Min	1,500
Elongation, Original	ASTM D412 – %	400

Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	- 50 % Max
Hardness Change	Points	± 15 Max

Oil Immersion

		No Requirement
--	--	----------------

Compression Set, Test Method ASTM D395 S, max, % 22 h @ 70 C

Compression Set	%	50% Max
-----------------	---	---------

Low-temperature resistance, Test Methods D2137, Method C, 9.3.3

Tests	Requirement	Result
	No Cracks	Pass